

## BAYSEAL<sup>®</sup> CCX/CCXP (Yellow Drum)

### Characterization

Bayseal closed-cell X (CC X) closed-cell is a spray-applied polyurethane foam (SPF) insulation.

### Properties / Applications

Bayseal closed-cell X (CC X) closed cell spray-applied polyurethane foam insulation is produced from a two component, HFC-245fa blown, medium density, structural system designed for commercial applications. Bayseal CCX/CCXP closed cell spray-applied polyurethane forms an integral part of any air barrier system.

The Bayseal CCX/CCXP foam is made with an "A" component or aromatic diisocyanate and a blended "B" component which includes polyols, fire retarding materials, and additives. Bayseal CCX/CCXP foam is available in two grades for warm and cold weather applications; suggested ambient temperatures are specified below:

Grade	Substrate/Ambient Temperature
Standard	50°F to 120°F
Polar	30°F to 70°F

### Storage Conditions

Material should be stored from 50°F to 80°F (10°C to 27°C) in a dry and well-ventilated area. Storage outside this range can affect shelf life and material performance. The material will need to be conditioned to between 70°F and 80°F (21°C and 27°C) prior to use. It takes approximately 48 hours in a heated area to condition all the material in a drum to the correct temperature.

Material temperature should be confirmed with a thermometer or an infrared gun. Do not configure equipment to recirculate Bayseal system components from proportioner back into drum. Do not recirculate or mix other suppliers' "B" component into Bayseal system containers.

**CAUTION: If components are below suggested temperatures, the increased viscosity of the components may cause pump cavitation resulting in unacceptable SPF application. If components are above suggested temperatures, there may be loss of blowing agent resulting in diminished yield.**

# BAYSEAL<sup>®</sup> CCX/CCXP (Yellow Drum)

## Typical Physical Properties\*

Properties**	Test Method	Value
Air Permeance at 75 Pa	ASTM E-2178	<0.02L/s-m <sup>2</sup>
Water Vapor Permeance	ASTM E-96 (B)	0.8 perm-in
		0.23 perms at 3.5"
		0.14 perms at 5.5"
		1.10 perms at 7.9"
Density	ASTM D-1622	2.0 lbs/ft <sup>3</sup> (Nominal)
Aged R-value, 6 months	ASTM C-518	6.9 at 1 inch
		21 at 3 inch
Compressive Strength	ASTM D-1621	25 psi
Tensile Strength	ASTM D-1623	60 psi
Water Absorption	ASTM D-2842	< 2% by volume
Dimensional Stability:	ASTM D-2126	
158°F @ 97% R.H		<9% Change in volume
Closed Cell Content	ASTM D-2856	> 90%
Surface Burning Characteristics <sup>a</sup> Flame Spread	ASTM E-84	<25
Surface Burning Characteristics <sup>a</sup> Smoke Index	ASTM E-84	<450
Fungi Resistance	ASTM G-21	Zero Rating

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

\*\* Prepared on a Graco H-40, 60-ft of hose using a GX7 with no. 1 mix module and 90 PCD, stream temperatures 120-125°F, pressure 1000 psi (dynamic).

<sup>a</sup> These numerical flame spread values are not a true reflection on how this or any material will perform in actual fire conditions.

<sup>b</sup> The higher the R-value, the greater the insulating power. Ask your seller for the fact sheet on R-values.



## BAYSEAL<sup>®</sup> CCX/CCXP (Yellow Drum)

### Processing Equipment

2:1 transfer pumps are recommended for material transfer from container to the proportioner. The plural component proportioner must be capable of supplying each component within  $\pm 2\%$  of the desired 1:1 mixing ratio by volume. Hose heaters should be set to deliver 110°F to 130°F materials to the spray gun. These settings will ensure thorough mixing in the spray gun mix chamber in typical applications. Optimum hose pressure and temperature will vary with equipment type and condition, ambient and substrate conditions, and the specific application. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates to the acceptable combinations of gun chamber size, proportioner output, and material pressures. The relationship between proper chamber size and the capacity of the proportioner's pre-heater is critical.

**CAUTION: Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.**

### Processing Parameters and Physical Characteristics

Pre-Heater Temperature:	"A" and "B"
CCX	"A" and "B" 105° - 120°F
CCXP	"A" and "B" 115° - 130°F
Hose Temperature:	"A" and "B"
CCX	"A" and "B" 105° - 120°F
CCXP	"A" and "B" 115° - 130°F
Pressures:	1,000 - 1,500 psi (dynamic)*
Mix Ratio Parts:	1 to 1 volume "A" to "B"
Viscosity at 75°F	400 - 500 cps "B" Component 150 - 250 cps "A" Component
Shelf Life	6 months @ 50°F to 80°F
<b>Or With Measuring Capabilities at Gun:</b>	
Material temperature at gun	"A" and "B" 100° - 120°F
Pressure at gun (w/in 15'	>800 psi

\* Dependent upon hose length.

## BAYSEAL<sup>®</sup> CCX/CCXP (Yellow Drum)

### Environmental Consideration and Substrate Temperatures

Applicators must recognize and anticipate environmental conditions prior to application to ensure the highest quality foam and to maximize yield. Ambient air and substrate temperature, moisture, and wind velocity are all critical determinants of foam quality and selection of the appropriate reactivity formulation. Variations in ambient air and substrate temperature will influence the chemical reaction of the two components, directly affecting the expansion rate, amount of rise, yield, adhesion and the resultant physical properties of the foam insulation.

To obtain optimum results, Bayseal CCX/CCXP foam should be spray-applied to substrates when ambient air and surface temperatures fall within the range of 30°F and 120°F. All substrates to be dry at the time of application. Moisture in the form of rain, fog, frost, dew, or high humidity (>85%R.H.), will react chemically with the mixed components, adversely affecting the polyurethane foam formation, dimensional stability, and physical properties of the finished product.

Wind velocities in excess of 12 miles per hour may result in excessive loss of exotherm and interfere with the mixing efficiency of the spray gun affecting foam surface texture, cure, and physical properties and will cause overspray. Precautions must be taken to prevent damage to adjacent areas from overspray.

---

### Per Lift Application

Applicators should apply a maximum pass thickness of 4 inches. Allow the surface temperature to cool to 100°F, or ambient temperature if higher than 100°F, between passes.

---

### Handling Information

Applicators should ensure the safety of the jobsite and construction personnel by posting appropriate signs warning that all "hot work " such as welding, soldering, and cutting with torches should not take place until a thermal barrier or approved equivalent is installed over any exposed polyurethane foam.

---

### Thermal Barrier

The International Building Code and International Residential Code requires that SPF be separated from the interior of a building by an approved fifteen (15) minute thermal barrier, such as 1/2" gypsum wall board or equivalent, installed per manufacturer's instructions and corresponding code requirements. The International Building Code allows for omission of the prescribed thermal barrier in certain instance, such as:

- attics and crawlspaces with limited access
  - approval by way of diversified testing, such as room corner protocols
- Local building codes may vary and must be consulted for applicability of thermal barrier exceptions.



## BAYSEAL<sup>®</sup> CCX/CCXP (Yellow Drum)

### Moisture Vapor Transmission (Permeance)

Bayseal CCX/CCXP qualifies as a vapor retarder as defined by the International Code Council and ASHRAE (Class II) at a minimum thickness of one inch. Building construction types with a persistent, high moisture drive require additional moisture remediation. The contractor should consult local building codes to establish the vapor retarder requirement.

---

### Additional Technical Reference

Construction Specification Institute Division 7 - Thermal and Moisture Protection

ICC- ES Evaluation Report ESR-2072

Bayseal CCX/CCXP Spray Polyurethane Foam (SPF) Installation Guidelines

---

### Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Accella Polyurethane Systems representative.



---

**DISCLAIMER:** To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Bayseal to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Bayseal. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY BAYSEAL EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.”

The information herein is to assist customers in determining whether our products are suitable for their applications. Customer assumes full responsibility for quality control, testing, and determination of suitability of product for its intended use or application. Accella warrants only that the material shall meet its specifications; this warranty is in lieu of all other written, expressed or implied warranties and Accella expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere to any recommended procedures shall relieve Accella of all liability with respect to the material or the use thereof.

---

Accella Polyurethane Systems  
2400 Spring Stuebner Rd  
Spring, TX 77377  
United States  
Tel. 1-800-221-3626