



September 1, 2015

**Subject: EcoBay/Bayseal STC & NRC Acoustic Data**

To Whom It May Concern:

As requested please find below the STC and NRC acoustic test data:

Covestro, LLC.  
2400 Spring Stuebner Rd.  
Spring, TX 77389

Office  
(281) 350-9000  
Toll Free  
(800) 221-3626  
Fax  
(281)288-5195

<u>Test</u>	<u>Test Procedure</u>	<u>OC Foam</u> 0.5 pcf	<u>CC Foam</u> 2.0 pcf
Sound Absorption, Noise Reduction Coefficient (NRC)	ASTM C-423	0.7	0.2
Sound Transmission Class (STC)	ASTM E-90	51	43

The test assembly consisted of wood studs and two layers of gypsum board on each side.

If you require further information please feel free to contact me directly.

Sincerely,

Richard R. Romero  
Covestro, LLC.

Spray Polyurethane Foam Insulation & Roofing Materials

Disclaimer: The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.