

DuPont™ RoofLiner

PHYSICAL PROPERTIES DATA SHEET

PROPERTIES	METHOD	VALUE
Liquid Water Transmission	ASTM D4869 (Section 8.3)	PASS
Basis Weight	TAPPI T410	4.6 oz/yd ²
Breaking Strength	ASTM D751	(MD) 120 lb _f (CD) 100 lb _f
Pliability	ICC-ES AC 48 (Section 3.0)	PASS
Accelerated Aging	ICC-ES AC 48 (Section 4.7)	PASS
Ultra Violet Exposure	ASTM G154	PASS
Fire Rating	ASTM E108	CLASS "A"
Tear Strength	ASTM D4533	(MD) 38 lb _f (CD) 31 lb _f

For more information about DuPont™ RoofLiner,
please call 1-800-448-9835
or visit us at www.roofing.dupont.com



The miracles of science™

DuPont™
RoofLiner