

# PERMABASE® BRAND PLUS™ CEMENT BOARD

## MANUFACTURER

National Gypsum Company  
2001 Rexford Road  
Charlotte, NC 28211  
(704) 365-7300

Technical Information:  
1-800-NATIONAL  
(1-800-628-4662)

Fax: 1-800-FAX NGC1  
(1-800-329-6421)

Internet Home Page:  
permabase.com  
nationalgypsum.com  
nationalgypsum.com/espanol  
09 28 00/NGC BuyLine: 1100

## DESCRIPTION

PermaBase® BRAND PLUS™ Cement Board is a lightweight, rigid substrate made of Portland cement, aggregate and glass mesh that provides an exceptionally hard, durable surface that is able to withstand prolonged exposure to moisture.

## BASIC USES

PermaBase PLUS is ideally suited as an underlayment or backing surface for tub and shower surrounds, countertops, flooring and a variety of other interior and exterior applications.

## ADVANTAGES

- PermaBase PLUS is up to 25% lighter than other cement boards on the market.
- Easier, cleaner cut.
- IBC/IRC Compliant. Manufactured in accordance with ASTM C 1325.
- Resists the growth of mold per ASTM D 3273 with a score of 10, the best possible score.
- Can be cut utilizing a standard utility knife and straightedge.
- PermaBase PLUS is impact resistant, extremely durable and dimensionally stable. It has excellent overall flexural, compressive and tensile strength characteristics.

- PermaBase PLUS is highly moisture resistant, and will not rot, disintegrate or swell when exposed to water.
- Approved for use in 1-hour and 2-hour rated assemblies and is UL Classified.
- Low water absorption.
- Suitable for both interior and exterior applications.

## MOLD AND MILDEW RESISTANCE

PermaBase PLUS was designed to provide extra protection against mold and mildew. When tested by an independent laboratory, PermaBase PLUS received the highest possible ratings on ASTM G 21 and D 3273. The use of PermaBase PLUS in actual installations may not produce the same results as were achieved in controlled laboratory conditions. No material can be considered "mold-proof," nor is it certain that any material will resist mold or mildew indefinitely. When used in conjunction with good design, handling and construction practices, PermaBase PLUS can provide increased mold resistance. As with any building material, avoiding water exposure during handling, storage

and installation, and after installation is complete, is the best way to avoid the formation of mold or mildew.

## LIMITATIONS

- Joints should be treated with alkali resistant fiberglass mesh tape set in a latex-Portland cement mortar.
- Conventional paper drywall tape, joint compound and drywall nails or screws should not be used.
- Maximum wall framing spacing should not exceed 16" o.c. and must be designed to limit deflection to L/360 under all live and dead loads.
- Steel framing must be 20 gauge (galvanized) or heavier-16 o.c.
- PermaBase PLUS is not a water barrier. Consult local building code for moisture barrier requirements.
- Not recommended for use with vinyl flooring.
- PermaBase PLUS should not be exposed to temperatures over 220°F (105°C).

## COMPOSITION & MATERIALS

Cementitious Backer Unit (CBU): PermaBase PLUS is a nailable, screwable backerboard or underlayment panel which is composed of Portland cement, aggregates and reinforcements that has a significant ability to remain unaffected by prolonged exposure to moisture.

## ACCESSORIES

*Joint reinforcement:* PermaBase mesh tape must be used on all edges and cuts made to size. Use 2" wide polymer-coated (alkali resistant) mesh tape for interior applications and 4" wide polymer-coated (alkali resistant) mesh tape for exterior applications.

*Bonding materials:* Treat joint and set facing material, preferably with latex-Portland cement mortar or with dry-set (thin-set) mortar. All mortars should comply with ANSI A118.1 or A118.4 standards. Type 1 organic adhesive meeting ANSI A-136.1 may be utilized for interior use only.

Job Name \_\_\_\_\_

Contractor \_\_\_\_\_ Date \_\_\_\_\_

Submittal Approvals: (Stamps or Signatures)

**Fasteners:** Galvanized roofing nails, 1-1/2" long with hot dipped galvanized coating for use with wood framing. Nails should meet Federal Specification #FF-N105B/ type 2 style 20.

PermaBase corrosion resistant screws or equivalent, 1-1/4" or 1-5/8" long, for use with wood framing. Type S-12 screws or equivalent, 1-1/4" or 1-5/8" long, for use with 20 gauge or heavier steel framing.

## TECHNICAL DATA

### Sizes & Packaging

Size: Thickness, Width & Length	# of Pcs. Per Unit
7/16" x 36" x 5' (11.1 mm x 914 mm x 1524 mm)	60

### PHYSICAL PROPERTIES

Property	Test Method	7/16" PermaBase Plus
Water Absorption % by Weight/24 Hours	ASTM C 473	10
Flexural Strength (psi)	ASTM C 947	750
Fastener Holding (Wet and Dry, lbs.)	ASTM D 1307 (0.400" head diameter)	90
Weight (psf)	ASTM C 473	2.1
Freeze/Thaw (cycles) per ANSI A118.9	ASTM C 666 Procedure B	100
Flame Spread/Smoke Developed	ASTM E 84	0/0
Fungus Resistance	ASTM G 21	(no growth)
Mold Growth on Surface	ASTM D 3273	10

### FIRE RESISTANCE RATINGS

**One-hour rating:** The one-hour wall assembly consists of 3-5/8" steel studs, 16" o.c., one layer of 7/16" PermaBase PLUS attached horizontally or vertically with 1-1/4" long cement board screws, 8" o.c. in the field and perimeter on one side and one layer of 5/8" Fire-Shield® BRAND Gypsum Board attached vertically, on opposite side, with joints staggered to those of opposite side, with 1-1/4" long drywall screws 8" o.c. in the field and perimeter side, with 3" thick mineral fiber insulation batts in the stud cavities. UL #V452.

**Two-hour fire rating:** The two-hour wall assembly consists of 3-5/8" steel studs, 16" o.c., on one side, base layer of 1/2" Fire-Shield C or 5/8" Fire-Shield Gypsum Board attached vertically with 1" drywall screws 24" o.c. in

the field and perimeter and face layer of 7/16" PermaBase PLUS attached vertically with 1-5/8" cement board screws, 8" o.c. in the field and perimeter. Two layers of 1/2" Fire-Shield C or 5/8" Fire-Shield Gypsum Board applied vertically to opposite side, base layer attached with 1" drywall screws 24" o.c. in the field and perimeter and face layer attached with 1-5/8" drywall screws 12" o.c. in the field and perimeter, with 3" thick mineral fiber insulation batts in the stud cavities. All joints staggered between face and base layer. UL #V452.

(Tests were conducted pursuant to ASTM E 119, as a non loadbearing wall, fire rated both sides under the supervision of Underwriters Laboratories.)

Additional Assemblies are available.

## INSTALLATION

### INTERIOR APPLICATIONS

**General:** All framing should comply with local building code requirements and be designed to provide support with a maximum allowable deflection of L/360 under all intended loads. Framing members should be spaced a maximum of 8" o.c.

**Note:** Cut or score PermaBase PLUS on printed side of panel. Install tile and tile setting materials in accordance with current ANSI specifications and Tile Council of North American (TCNA) guidelines.

**Control joints:** For interior installations, allow a maximum of 30 lineal feet between control joints. A control joint must be installed but not limited to the following locations: where expansion joints occur in the framing or building (discontinue all cross furring members located behind joint); when boards abut dissimilar materials; where framing material changes; at changes of building shape or structural system; at each story separation. Place control joints at corners of window and door openings, or follow specifications of architect. Control joint cavity shall not be filled with coating or other materials.

### Walls & Ceilings

**Wall framing:** Edges of PermaBase PLUS parallel to framing should be continuously supported. Provide additional blocking when necessary to permit proper PermaBase PLUS attachment.

Do not install PermaBase PLUS directly over protrusions from stud plane such as heavy brackets or fastener heads. Studs above a shower floor should be either notched or furred to accommodate the thickness of the waterproof membrane or pan. The surround opening for a tub or precast shower receptor should not be more than 1/4" longer than unit to be installed.

**Ceiling framing:** The deflection of the complete ceiling assembly due to dead load (including insulation, PermaBase PLUS bonding

material and facing material) should not exceed L/360. The dead load applied to the ceiling frame should not exceed 10 psf. Ceiling joist or furring channel should not exceed 16" o.c. (Edges of PermaBase PLUS parallel to framing should be continuously supported.) Provide additional blocking when necessary to permit proper PermaBase PLUS attachment.

**PermaBase PLUS Cement Board:** Apply PermaBase PLUS with ends and edges closely butted, but not forced, together. Stagger end joints in successive courses. Drive fasteners into field of cement board first, working toward ends and edges. Space fasteners maximum 8" o.c. for walls, 6" o.c. for ceilings with perimeter fasteners at least 3/8" and less than 5/8" from ends and edges. Ensure PermaBase PLUS is tight to framing.

**Joint reinforcement:** Trowel bonding material to completely fill the tapered recessed board joints and gaps between each panel. On non-tapered joints, apply a 6" wide, approx. 1/16" thick coat of bonding material over entire joint. For all joints, immediately embed 2" alkali-resistant fiberglass mesh tape fully into applied bonding material and allow to cure. Same bonding material should be applied to corners, control joints, trims or other accessories. Feather bonding material over fasteners to fully conceal.

### Floors & Counters

**Subfloor or Base:** For flooring applications with 16" o.c. floor joists, 5/8" tongue and groove exterior grade plywood or 3/4" tongue and groove exterior grade OSB may be used. For 19.2" o.c. and 24" o.c. floor joists, 3/4" tongue and groove exterior grade plywood or OSB must be used. Tile size for floors with 24" o.c. floor joists must be 12" x 12" or larger. The joists and subfloor assembly must meet L/360, as well as the appropriate code tables, for live and dead loads.

**Underlayment:** Using a 1/4" square-notched trowel, apply a setting bed of Latex-Portland Cement

mortar or Thin-Set mortar to the subfloor or counter base. Immediately laminate PermaBase PLUS to subfloor or base leaving a 1/8" space between boards at all joints and corners. Leave a 1/4" gap along walls. Stagger joints so they do not line up with underlying substrate joints. Fasten PermaBase PLUS every 8" o.c. throughout board field and around all edges while setting bed mortar is still workable. Around perimeter of each board, locate fasteners 2" from the corners and not less than 3/8" from the edges. Fill all joints solid with bonding material. On non-tapered joints such as butt ends, apply a 6" wide, 1/16" thick coat over the entire joint. For all joints, embed fiberglass mesh tape fully into applied bonding material; ensure that tape is centered over joint. Apply bonding material over fasteners to fully conceal. Remove all excess bonding material and allow to cure.

over joint. Apply bonding material over fasteners to fully conceal. Remove all excess bonding material and allow to cure.

*Waterproof membrane:* Trowel apply waterproof membrane to the entire surface of the PermaBase PLUS following membrane manufacturer's installation instructions in detail.

## **Decks**

*Subfloor:* Plywood should be securely glued and fastened to floor joists spaced a maximum of 16" o.c. Subfloor should be sloped at a minimum pitch of 1/4" per foot. The floor surface should be true to plane within 1/8" in 10'.

*Underlayment:* Using a 1/4" square-notched trowel, apply a setting bed of Latex-Portland Cement mortar to the subfloor. Immediately laminate PermaBase PLUS to subfloor leaving a 1/8" space between boards at all joints and corners. Leave a 1/4" gap along walls. Stagger joints so they do not line up with underlying substrate joints. Fasten PermaBase PLUS every 8" o.c. throughout board field and around all edges while setting bed mortar is still workable. Around perimeter of each board, locate fasteners 2" from the corners and not less than 3/8" from the edges. Fill all joints solid with bonding material. On non-tapered joints such as butt ends, apply a 6" wide, 1/16" thick coat over the entire joint. For all joints, embed alkali-resistant fiberglass mesh tape fully into applied bonding material; ensure that tape is centered

