

DUPONT™ TYVEK® DRAINVENT™ RAINSCREEN

PHYSICAL PROPERTIES

Property	Test Method	Unit	Value
Composite Mass/Unit Area	ASTM D5261	oz/yd ² (g/m ²)	12.2 (413)
Composite Thickness	ASTM D6525	in (mm)	0.27 (6.8)
Core Width	ASTM D3774	in (m)	48 (1.2)
Roll Weight	NA	lbs (kg)	16.0 (7.2)
Roll Length	NA	ft (m)	50 (15.2)
Roll Coverage	NA	ft ² (m ²)	200 (18.6)
Breaking Strength (Filter Fabric) MD	ASTM D5034	lb/in (N/2.54 cm)	42.7 (190)
Breaking Strength (Filter Fabric) CD	ASTM D5034	lb/in (N/2.54 cm)	32.6 (145)
Surface Burning Characteristics	ASTM E84	Flame Spread Index	15 Class A
Surface Burning Characteristics	ASTM E84	Smoke Developed Index	115 Class A
Max Ultra Violet Light Exposure (UV)	ASTM G90	days	90

For more information about
 DuPont™ Tyvek® DrainVent™ Rainscreen, please call
 1-800-44-Tyvek or visit us at drainvent.tyvek.com