



PANGO® BOND

A STEGO TECHNOLOGY, LLC INNOVATION | VAPOR BARRIER 31 31 16, 07 26 00, 03 30 00 | VERSION: OCT 23, 2020

1. PRODUCT NAME

PANGO BOND

2. MANUFACTURER

c/o Stego® Industries, LLC*
 216 Avenida Fabricante, Suite 101
 San Clemente, CA 92672
 Sales, Technical Assistance
 Ph: (877) 464-7834
 Fx: (949) 257-4113
 www.stegoindustries.com



3. PRODUCT DESCRIPTION

USES: Pango Bond is designed to be used as a physical barrier to subterranean termites in conjunction with Pango® Wrap and Pango Claw® and Pango® Term Bar. Pango Bond can be used as an alternate to detail patches for penetrations in Pango Wrap and to seal to foundation constructions.

COMPOSITION: Pango Bond is a two-component, 100% solids, semi-rigid epoxy sealant.

SIZE: Pango Bond comes in a 4-gallon kit size: Two 1-gallon cans of Part A (Resin) and two 1-gallon cans of Part B (Hardener).

COVERAGE: 96ft² @ 60-mils per kit (4 gallons of product).

4. TECHNICAL DATA

TABLE 4.1: PHYSICAL PROPERTIES OF PANGO BOND

PROPERTY	TEST	RESULTS
Mix Ratio (A:B by volume)		1:1
Mixed Viscosity		Gel
Gel Time (100 g)		50-60 mins
Pot Life (full unit)		30-45 mins
Tack Free Time		5-6 hours
Shore A Hardness	ASTM D2240	80-90
Tensile Strength	ASTM D638	800 psi
Tensile Elongation %	ASTM D638	95-105%
Water Vapor Permeance	ASTM F1249	0.015 perms @ 60-mils

Note: perm unit = grains/(ft²*hr*in-Hg)
 All data are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

5. INSTALLATION

PREPARATION:

- A test application simulating the project environment should always be done prior to final usage of Pango Bond.
- All surfaces should be dry and free of loose materials, oils, and other contaminants. The surfaces should be cleaned in the same fashion as the test surface in order to ensure proper application.
- Pango Bond can be applied by trowel or bulk caulking gun at various spread rates. Optimum ambient temperature is between 50-90°F during application. Note: Cure times are affected by ambient and surface temperatures. Temperatures of 40°F and lower can slow cure times. Temperatures of 90°F and higher will speed up cured times and reduce working time.

PANGO® BOND

A STEGO TECHNOLOGY, LLC INNOVATION | VAPOR BARRIER 31 31 16, 07 26 00, 03 30 00 | VERSION: OCT 23, 2020

5. INSTALLATION *Continued...*

PREPARATION *Continued...*

- Mix the following with a drill and mixing paddle (Note: If using a drill mixer, use a low speed [not to exceed 300 rpm] to prevent air entrapment):
 - Premix Part A and Part B separately. Combine 1 part by volume of Part A to 1 part by volume of Part B and mix thoroughly. Do not thin. Scrape the side and bottom of the mixing container to assure uniform and complete mixing. Mix for 2-3 minutes. Do not aerate mix.

TO FOUNDATIONS: Apply Pango Bond along the wall or other surface just below the anticipated height of the terminating edge of Pango Wrap. Apply Pango Bond in a continuous bead such that, when the wrap is pressed against Pango Bond, a roughly 2-inch wide continuous strip will be created behind the subsequently applied Pango Term Bar. Press Pango Wrap firmly against Pango Bond and utilize Pango Term Bar to secure in place. Apply additional Pango Bond over the lip of the wrap and/or Pango Term Bar to ensure a consistent seal.

PENETRATIONS: To repair around multiple or single penetrations in Pango Wrap, cut a hole in Pango Wrap that minimizes the void space between the edge of the outermost penetrations and the edge of Pango Wrap. Install Pango Claw within one inch of the edge of the wrap, following its contour as best as possible, while avoiding overlapping Pango Claw onto itself. Apply Pango Bond against the penetration(s) and over the adjacent wrap, extending Pango Bond at least an inch over Pango Claw's textured surface. Apply sufficient Pango Bond to create a continuous mass that extends from its terminating point over Pango Claw and slopes uniformly up each encompassed penetration.

Review Pango Wrap's complete installation instructions prior to installation.

6. AVAILABILITY & COST

Pango Bond is available through our network of building supply distributors. For current cost information, contact your local Pango distributor or Stego Industries' Sales Representative.*

7. WARRANTY

Stego Industries, LLC believes to the best of its knowledge, that specifications and recommendations herein are accurate and reliable. However, since site conditions are not within its control, Stego Industries does not guarantee results from the use of the information provided and disclaims all liability from any loss or damage. Stego Technology, LLC does offer a limited warranty on Pango Wrap. Please see www.stegoindustries.com/legal.

8. MAINTENANCE

Store locked up in a dry and temperate area.

9. TECHNICAL SERVICES

Technical advice, custom CAD drawings, and additional information can be obtained by contacting Stego Industries or by visiting the website.

Contact Number: [877] 464-7834

Website: www.stegoindustries.com

10. FILING SYSTEMS

- www.stegoindustries.com

[877] 464-7834 | www.stegoindustries.com

DATA SHEETS ARE SUBJECT TO CHANGE. FOR MOST CURRENT VERSION, VISIT WWW.STEGOINDUSTRIES.COM

